

WESTERN PLASTICS

41573 DENDY PKWY TEMECULA, CA 92590

Telephone (951) 695-1983 Fax (951) 695-2004 Wats (800) 442-9727 e-Mail: western@wplastics.com

Web: www.wplastics.com

Dissipative Stretch Wrap Specifications

Tensile

Stretch Film

Ultimate

Yield

	mil	lbs	psi	%elong	lbs	psi	%elong
MD	0.78	7.1	9100	680	1.2	1570	62
TD	0.83	4.7	5680	1050	1.0	1200	18

2% Secant Modulus

	mil	psi
MD	0.71	17690
TD	0.80	18480

Spencer Impact

Avg 16.040

Tear

MD 371 g Stretches & Oblique Tears

TD 585 g Stretches & Oblique Tears

Puncture - FED TEST 101C, Method 2065

	mil	lbs/force	elong
Avg	0.85	4.1	2.4

Static Decay - FED STD 101C, Method 4046

± 5KV Less than 2 seconds

Surface Resistivity - 10_{11} ohm/square nom

ASTM D 257

Standard Sizes

Handwrap

4 rolls per case

17.5" 80 ga 1500' 36 cs/plt

Machine Grade

40 rolls per pallet

20" 80 ga 5000'

Average Lead Time: 2 weeks

DISCLAIMER - SELLER MAKES NO WARRANTY, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE, except that the product shall conform to contracted specifications. Determination of the suitability of the product for the uses and applications contemplated by the Buyer and others shall be the sole responsibility of Buyer. Buyer's exclusive remedy shall be for damages and no claim of any kind, whether as to product delivered or for non-delivery of product, and whether based on contract, breach of warranty, negligence or otherwise shall be greater in amount than the purchase price of the quantity of the product in respect of which damages are claimed. In no event shall Seller be liable for incidental or consequential damages, whether Buyer's claim is based on contract, breach of warranty, negligence or otherwise.