

# WESTERN PLASTICS

41995 REMINGTON AVENUE • TEMECULA, CA 92590  
Phone (800) 442-9727 • Fax (951) 695-2004 • e-mail: info@wplastics.com  
wplastics.com

## Product Data Sheet Perform XL

Property	ASTM Method	Value
Thickness (Mil)		0.50
Haze	D-1003	1.4
Cling (Grams)	D-5458	105 tgt.
<b>Tensile Properties</b>	<b>D-882</b>	
Elongation % (MD)	D-882	410%
Elongation % (TD)	D-882	580%
Tensile Yield (MD)	D-882	1600 PSI
Tensile Yield (TD)	D-882	1500 PSI
Tensile Ultimate (MD)	D-882	6300 PSI
Tensile Ultimate (TD)	D-882	4300 PSI
Puncture Resistance	D-4649	7.5 Lbf-Inch
Ultimate Stretch	Highlight Industries	360%

These are typical properties; not to be construed as specification limits