

WESTERN PLASTICS

Product and Technical Information Typical Values

Western Plastics Laundry Wrap

Properties	Units	Test Reference	Value
Yield	Sq. invib.	n/a	48,500
Tensile Strength	Lbs. in. M.D. Lbs. in. T.D.	ASTM-D-882-75B Method A	6200 5400
Elongation	% M.D. % T.D.	ASTM-D-882-76B	270 310
Water Vapor Transmission Rate	Gms/100 sq.in. Per 24 hrs. @ 100° F, 90% RH	ASTM-E-96-66	24.0
Gas Transmission O2 CO2	Cc/100 sq. in. per 24 hrs.	Modern Controls Oxtran 100 @ 23° C	825
		Linde Cell @ 23° C 1 atmosphere	7,700
Heat Seal Range	° F	Sentinel Sealer 30 psi, 0.5 sec.	280 - 330
Non Fog Property	n/a	n/a	Yes
Haze	%	ASTM-D-1003-61	1.0

Disclaimer

The information and recommendations contained herein are offered as a service to our customers, but are not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of these materials. The information and recommendations provided herein were believed by Western Plastics to be accurate at the time of preparation or obtained from sources believed to be generally reliable. However, Western Plastics makes no warranty concerning their accuracy and Western Plastics will not be liable for claims relating to any party's use or reliance on information or recommendations contained herein; regardless of whether it is claimed that the information or recommendations are inaccurate, incomplete or otherwise misleading.

Western Plastics, Georgia

2399 US 41 SW
Calhoun, GA, 30701
Tel: (706) 625-5260
Fax: (706) 625-0003
Wats: (800) 752-4106

Western Plastics, California

41573 Dendy Parkway
Temecula, CA 92590
Tel: (951) 695-1983
Fax: (951) 695-2004
Wats: (800) 442-9727