

# **WESTERN PLASTICS**

## **General Specifications**

**GRADE: Tinted/Opaque Machine Film**

**TYPE: BLOWN HIGH QUALITY**

<b>TEST</b>	<b>63 Gauge</b>	<b>ASTM TEST METHODS</b>
<b>TENSILE TEST</b> TENSILE @ YIELD MD TENSILE @ YIELD TD	1,600 PSI 1,700 PSI	D-882
TENSILE STRENGTH MD TENSILE STRENGTH TD	6,900 PSI 4,900 PSI	
ELONGATION MD ELONGATION TD	450% 600%	
<b>TEAR TEST</b> ELMENDORF MD ELMENDORF TD	140 G / MIL 700 G / MIL	D-1922
<b>PUNCTURE TEST</b> FORCE ENERGY ENERGY / THICKNESS	7.5 LBS 15.8 IN-LBS 25.0 IN-LBS/MIL	D-4649 A5
<b>OTHER</b> YIELD	47,600 SQ.IN/LB	

**Note: MD = Machine Direction TD = Tranverse Direction**