

WESTERN PLASTICS

20/63/5000 HIGH PERF. IDENTI-FILM

<i>PROPERTY</i>	<i>TEST METHOD REFERENCE</i>	<i>VALUES</i>
Gauge, mil	ASTM D-374	0.60
Ult Tensile MD, psi	ASTM D-882	5400
Ult Tensile TD, psi	ASTM D-882	3400
Tens Yield MD, psi	ASTM D-882	1450
Tens Yield TD, psi	ASTM D-882	1350
Ult Elong MD, %	ASTM D-882	370
Ult Elong TD, %	ASMT D-882	560
1% Modulus MD, psi	ASMT D-882	25000
1% Modulus TD, psi	ASTM D-882	30000
Tear MD, g	ASTM D-1922	180
Tear TD, g	ASTM D-1922	500
Puncture, lbs	Internal	7.8
Dart Impact F50, g	ASTM D-1709A	80

The data presented above are based on random tests performed at the time of manufacture and should not be considered as limiting specifications. There is no guarantee expressed or implied regarding the use for this information or its suitability for a particular application