



Perform XL

Technical Data

Gauge		50	55	60	70	80	90	115	Test Method
Elmendorf Tear (Gms./Sht)	MD	125	130	150	175	225	250	340	ASTM D1922
	TD	330	443	450	475	500	525	570	
Haze (%)		1.2	1.4	1.6	1.9	2.1	2.3	2.6	ASTM D1003
Gloss 45 (%)		91	88	90	90	88	88	87	ASTMD 2457
Ultimate Tensile (PSI)	MD	7050	7321	7200	7000	6800	6500	6000	ASTM D882
	TD	4400	4400	4400	4400	4400	4400	4400	
Maximum Elongation (%)	MD	480	549	550	575	600	625	650	ASTM D882
	TD	770	780	800	850	875	900	925	
Dart Drop (Gms./Sht)		90	94	100	110	125	140	165	ASTM D1709
Highlight Wrapper Stretch	%	210	220	255	290	300	310	330	Highlight
Instron Cling	Gms	100 to 145 for all gauges and depend on stretch %							CFP62023-3-028