

WESTERN PLASTICS

General Specifications

GRADE: BLACK OPAQUE HAND FILM

TYPE: BLOWN HIGH QUALITY

TEST	80 Gauge	ASTM TEST METHODS
TENSILE TEST TENSILE @ YIELD MD TENSILE @ YIELD TD	1,600 PSI 1,700 PSI	D-882
TENSILE STRENGTH MD TENSILE STRENGTH TD	6,600 PSI 4,000 PSI	
ELONGATION MD ELONGATION TD	450% 600%	
TEAR TEST ELMENDORF MD ELMENDORF TD	120 G / MIL 650 G / MIL	D-1922
PUNCTURE TEST FORCE ENERGY ENERGY / THICKNESS	8.3 LBS 16.0 IN-LBS 20.0 IN-LBS/MIL	D-4649 A5
CLING TEST IN TO OUT	Min. 150 G	D-5458
OTHER YIELD	37,500 SQ.IN/LB	

Note: MD = Machine Direction TD = Transverse Direction

Manufactured with pride in the USA